

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
877.798.6666



Ryton[®] BR111

Polyphenylene Sulfide Resins

Ryton[®] BR111 and BR111BL PPS are glass and mineral filled polyphenylene sulfide compounds developed to provide a good combination of mechanical strength and electrical properties.

| Nominal Engineering Properties ⁽¹⁾ | BR111 | BR111BL | Test Method |
|--|----------------------|----------------------|-------------|
| Tensile Strength, Ksi | 24.0 | 22.0 | ASTM D638 |
| Elongation, % | 1.1 | 1.0 | ASTM D638 |
| Flexural Strength, Ksi | 36.0 | 34.0 | ASTM D790 |
| Flexural Modulus, Msi | 2.8 | 2.8 | ASTM D790 |
| Notched Izod Impact, ft-lb/in, 1/8 in specimen | 1.3 | 1.2 | ASTM D256 |
| Unnotched Izod Impact, ft-lb/in, 1/8 in specimen | 6.5 | 5.5 | ASTM D256 |
| Compressive Strength, Ksi | 43.0 | 43.0 | ASTM D695 |
| Heat Deflection Temperature 264 psi, °F | >500 | >500 | ASTM D648 |
| UL Temperature Index, °C | 220 / 240 | 220 / 240 | UL 746B |
| Coefficient of Linear Thermal Exp., X 10 ⁶ in/in/°C | | | ASTM E831 |
| Axial Direction, -50°C to 50°C | 15 | 15 | |
| Axial Direction, 100°C to 200°C | 10 | 10 | |
| Transverse Direction, -50°C to 50°C | 30 | 30 | |
| Transverse Direction, 100°C to 200°C | 70 | 70 | |
| Flammability Rating | V-0 | V-0 | UL 94 |
| Thermal Conductivity, BTU-in/hr-ft ² -°F | 3.5 | 3.5 | |
| Dielectric Strength, V/mil | 450 | 450 | ASTM D149 |
| Dielectric Constant, 78° F | | | ASTM D150 |
| 1kHz | 4.6 | 4.6 | |
| 1MHz | 4.6 | 4.6 | |
| Dissipation Factor, 78°F | | | ASTM D150 |
| 1 kHz | 0.002 | 0.002 | |
| 1 MHz | 0.003 | 0.003 | |
| Volume Resistivity, ohm-cm | 1 x 10 ¹⁵ | 1 x 10 ¹⁵ | ASTM D257 |
| Arc Resistance, sec | 180 | 180 | ASTM D495 |
| Comparative Tracking Index, V | 225 | 225 | UL 746A |
| Insulation Resistance, ohm (90°C, 95% RH, 48 hr) | 1 x 10 ¹⁰ | 1 x 10 ¹⁰ | |
| Mold Shrinkage ⁽²⁾ in/in, Flow/Transverse | 0.002 / 0.005 | 0.002 / 0.005 | |
| Density, g/cc | 1.94 | 1.94 | ASTM D792 |
| Water Absorption, % | 0.02 | 0.02 | ASTM D570 |
| Color | Natural | Black | |

(1) Test specimen molding conditions: Stock Temperature, 600-650° F; Mold Temperature, 275° F

(2) Measured on 4 in X 4 in X 1/8 in Plaques, Edge Gated

The nominal properties reported herein are typical of the product but do not reflect normal testing variances and therefore should not be used for specification purposes.

MSDS #440880

Revision Date January, 2008

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
877.798.6666



Ryton[®] BR111

Polyphenylene Sulfide Resins

Ryton[®] BR111 and BR111BL PPS are glass and mineral filled polyphenylene sulfide compounds developed to provide a good combination of mechanical strength and electrical properties.

| Nominal Engineering Properties ⁽⁵⁾ | BR111 | BR111BL | Method |
|--|----------------------|----------------------|-------------|
| Tensile Strength, MPa | 165 | 155 | ISO 527 |
| Elongation, % | 1.1 | 1.0 | ISO 527 |
| Flexural Strength, MPa | 245 | 230 | ISO 178 |
| Flexural Modulus, GPa | 19 | 19 | ISO 178 |
| Notched Izod Impact, kJ/m ² | 7.0 | 6.5 | ISO 180A |
| Unnotched Izod Impact, kJ/m ² | 25 | 20 | ISO 180U |
| Compressive Strength, MPa | 295 | 295 | ISO 604 |
| Heat Deflection Temperature 1.8 MPa, °C | >260 | >260 | ISO 75 |
| UL Temperature Index, °C | 220 / 240 | 220 / 240 | UL 746B |
| Coefficient of Linear Thermal Exp., X 10 ⁶ m/m/°C | | | ISO 11359-2 |
| Axial Direction, -50°C to 50°C | 15 | 15 | |
| Axial Direction, 100°C to 200°C | 10 | 10 | |
| Transverse Direction, -50°C to 50°C | 30 | 30 | |
| Transverse Direction, 100°C to 200°C | 70 | 70 | |
| Flammability Rating | V-0 | V-0 | UL 94 |
| Thermal Conductivity, W/m·K | 0.51 | 0.51 | |
| Dielectric Strength, kV/mm | 18 | 18 | ASTM D149 |
| Dielectric Constant, 25°C | | | ASTM D150 |
| 1kHz | 4.6 | 4.6 | |
| 1MHz | 4.6 | 4.6 | |
| Dissipation Factor, 25°C | | | ASTM D150 |
| 1 kHz | 0.002 | 0.002 | |
| 1 MHz | 0.003 | 0.003 | |
| Volume Resistivity, ohm·cm | 1 x 10 ¹⁵ | 1 x 10 ¹⁵ | ASTM D257 |
| Arc Resistance, sec | 180 | 180 | ASTM D495 |
| Comparative Tracking Index, V | 225 | 225 | UL 746A |
| Insulation Resistance, ohm (90°C, 95% RH, 48 hr) | 1 x 10 ¹⁰ | 1 x 10 ¹⁰ | |
| Mold Shrinkage ⁽⁶⁾ m/m, Flow/Transverse | 0.002 / 0.005 | 0.002 / 0.005 | |
| Density, g/cc | 1.94 | 1.94 | ISO 1183A |
| Water Absorption, % | 0.02 | 0.02 | ASTM D570 |
| Color | Natural | Black | |

(5) Test specimen molding conditions: Stock Temperature, 315 - 345° C; Mold Temperature, 135° C

(6) Measured on 102 mm X 102 mm X 3.2 mm Plaques, Edge Gated

The nominal properties reported herein are typical of the product but do not reflect normal testing variances and therefore should not be used for specification purposes.

MSDS #440880

Revision Date January, 2008

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.