

## Noryl\* Resin V0150B

### Europe-Africa-Middle East: COMMERCIAL

Noryl\* V0150B is an unfilled, injection moldable modified polyphenylene ether resin.. Designed for high heat resistance and thin wall FR performance, this resin delivers a UL94 V0 rating at 1.5 mm and a UL94 5Va rating at 2.0 mm. Noryl V0150B is also halogen free according to VDE/DIN 472 part 815 and may be an excellent material candidate where flame resistance and high temperature resistance is required.

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	UNIT	STANDARD
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	710	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	610	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Modulus, 5 mm/min	25400	kgf/cm <sup>2</sup>	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1070	kgf/cm <sup>2</sup>	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	26000	kgf/cm <sup>2</sup>	ASTM D 790
Taber Abrasion, CS-17, 1 kg	35	mg/1000cy	SABIC Method
Tensile Stress, yield, 50 mm/min	70	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	110	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
Hardness, H358/30	113	MPa	ISO 2039-1
<b>IMPACT</b>			
Izod Impact, notched, 23°C	33	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	18	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	509	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	13	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m <sup>2</sup>	ISO 180/1A

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

Source, GMD, Last Update: 01/19/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC Innovative Plastics IP BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Noryl is a trademark of SABIC INNOVATIVE PLASTICS HOLDING BV

© 1997-2008 SABIC INNOVATIVE PLASTICS HOLDING BV. All rights reserved

## Noryl\* Resin V0150B

### Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	UNIT	STANDARD
<b>IMPACT</b>			
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	155	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.27	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	140	°C	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	160	°C	ISO 306
Vicat Softening Temp, Rate B/50	145	°C	ISO 306
Vicat Softening Temp, Rate B/120	155	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	140	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	130	°C	ISO 75/Ae
Relative Temp Index, Elec	110	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	115	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.11	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow (2)	0.5 - 0.7	%	SABIC Method
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 280°C/5.0 kgf	3.5	g/10 min	ASTM D 1238

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

Source, GMD, Last Update: 01/19/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Noryl is a trademark of SABIC Innovative Plastics IP BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved

## Noryl\* Resin V0150B

### Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	UNIT	STANDARD
<b>PHYSICAL</b>			
Density	1.11	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.18	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	10	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0	-	IEC 60250
Dissipation Factor, 1 MHz	0.003	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94-5VA Rating (3)	2	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	32	%	ISO 4589

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

Source, GMD, Last Update: 01/19/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Noryl is a trademark of SABIC Innovative Plastics IP BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved

## Noryl\* Resin V0150B

### Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
<b>Injection Molding</b>		
Drying Temperature	110 - 120	°C
Drying Time	2 - 3	hrs
Melt Temperature	300 - 320	°C
Nozzle Temperature	280 - 300	°C
Front - Zone 3 Temperature	300 - 320	°C
Middle - Zone 2 Temperature	280 - 300	°C
Rear - Zone 1 Temperature	260 - 280	°C
Hopper Temperature	80 - 100	°C
Mold Temperature	100 - 130	°C

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.  
All properties, except the melt volume rate are measured on injection moulded samples.  
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.  
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.  
4) Own measurement according to UL.

Source, GMD, Last Update: 01/19/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Noryl is a trademark of SABIC Innovative Plastics IP BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved

**Noryl\* Resin V0150B**

**Europe-Africa-Middle East: COMMERCIAL**


**CALCULATED FLOW LENGTH INDICATION**

**Moldflow® Radial Flow Analysis**

**Noryl® V0150B**

**Melt Temperature : 310°C**

**Mold Temperature : 90°C**



**Note: Technical support is recommended if Gate Pressure is greater than 80 MPa. Contact your local representative.**

**® Moldflow is a registered trademark of the Moldflow Corporation.**

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.  
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.  
4) Own measurement according to UL.

Source, GMD, Last Update: 01/19/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Noryl is a trademark of SABIC Innovative Plastics IP BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved